



Neodymium Iron Boron / Magnetic Properties									
Grade	Press <sup>1</sup>	Br (Gauss)	Hc (Oersteds)	Hci (Oersteds)	BHmax (MGOe)	Temperature Coefficients (%/°C)		Maximum Operating Temp @ Pc=2 <sup>(2)</sup>	
		Range	Typical	Minimum	Range	of BR	of Hci	(°C)	(°F)
N4614	D	13,300 ~ 13,800	12,200	14,000	42 ~ 46	-0.11	-0.61	~ 130	~ 260

<sup>1</sup> D: Die-Pressed, I: Isostatically-Pressed

<sup>2</sup> The Maximum Operating Temperature shown here is for magnets operating at a Permeance Coefficient of 2. At the temperatures shown the operating point of the material is above the knee of the BH Curve.

Neodymium Iron Boron / Physical Properties											
Grade	Density		Bending Strength		Compressive Strength		Electrical Resistivity (Ωm)	Coeff. of Thermal Expansion <sup>3</sup>		Curie Temperature	
	(Kg/m <sup>3</sup> )	(lbs/in <sup>3</sup> )	(kg/m <sup>2</sup> )	(lbs/in <sup>2</sup> )	(kg/m <sup>2</sup> )	(lbs/in <sup>2</sup> )		// M	⊥M	(°C)	(°F)
N4614	7.6 x 10 <sup>3</sup>	0.275	2.95 x 10 <sup>3</sup>	4.2 x 10 <sup>4</sup>	9.6 x 10 <sup>3</sup>	1.3 x 10 <sup>5</sup>	1.4 x 10 <sup>-6</sup>	7.4 x 10 <sup>-6</sup>	-1.1 x 10 <sup>-6</sup>	340	640

<sup>3</sup>// M Parallel to magnetic orientation, ⊥M Perpendicular to magnetic orientation.